



CUSTOM SOLUTIONS

MEGABITE

Strips Residue-Free – Won't Interfere with Finish Application

No Floor Rinse Required – Saves Time and Labor

Penetrates Quickly – Turn Floors Over Fast

TIME AND LABOR SAVING STRIPPER

Professional Recommendations

- Schedule stripping your floor based on traffic wear and desired appearance
- **Do not** buff a bare dry floor before coating – you may release asbestos into the air
- **Do not** strip linoleum or rubber tiles with this product; it will remove binding oils and embrittle the floor
- **Do not** use at stronger dilutions than recommended – the stripping solution will dry too quickly on the floor, possible re-hardening and causing removal problems
- Always at least damp mop residual stripping solution – "Rinse Free" only means no floor rinse is required

Specifications


Appearance	Clear opal liquid
Odor	Citrus
Density (lb/gal)(±0.05 @20°C)	8.30
pH (conc.)(±0.5@20°C)	12.5
Flashpoint	178°F
Stability (40°-120°F)	Stable
Freeze/thaw stability	OK 3 cycles
Shelf life	1 year minimum
D.O.T. Hazard class	Corrosive

Equipment List

- ✓ Wet floor signs
- ✓ Single disc floor machine or autoscrubber
- ✓ Wet vacuum
- ✓ Black, brown or high productivity pads
- ✓ Looped-end cotton mop
- ✓ Mop bucket with wringer, dust mop
- ✓ Edge tool
- ✓ Scraper
- ✓ Walk-off towel
- ✓ Squeegee

Available in sizes:
1, 2.5, 55 gallon and tote containers.

Wear safety equipment recommended on MSDS, place wet floor signs and read all directions and cautions prior to beginning work.



Dilute **MegaBite** with warm water 2:1 for no-scrub bare floor stripping (64 oz. per gallon), 4:1 for bare floor stripping (20 oz. per gallon). Apply to surface liberally.



Allow 5-10 minutes for stripper to work.



Do not allow solution to dry. If preferred, use a stripping pad on an autoscrubber or single disk floor machine. Scrub thoroughly to remove all old coatings.



Check edges and baseboards for buildup. Remove with doodlebug or pad center. Scrub and pick up with autoscrubber or wet vac. Damp mop lightly with cool water to remove all residues. Allow floor to dry before recoating.

